

# Evaluation of thermal conductivity of COOH-functionalized MWCNTs/water via temperature and solid volume fraction by using experimental data and ANN methods

Mohammad Hemmat Esfe · Ali Naderi ·  
Mohammad Akbari · Masoud Afrand ·  
Arash Karimipour

Received: 1 January 2015 / Accepted: 12 February 2015 / Published online: 28 March 2015  
© Akadémiai Kiadó, Budapest, Hungary 2015

**Abstract** In the present study, the results of several experiments have been used to obtain the thermal conductivity of multi walls carbon nanotubes-water nanofluid. For this purpose, COOH-functionalized MWCNTs nanoparticles have divided into different solid volume fractions in order to disperse in water as the base fluid by different dispersion methods. The thermal conductivity measurement applied in different solid concentrations, up to 1 %, and at the temperatures ranging from 25 to 55 °C. In this paper, based on the experimental data, a new correlation for predicting the thermal conductivity of COOH-functionalized MWCNTs/water nanofluid proposed. After that, for simulating the thermal conductivity of this nanofluid, the artificial neural network is used. For this purpose, multilayer perceptron neural network is used. The network input variables are temperature and solid volume fraction, and the network output variable is thermal conductivity. The results extracted from the artificial neural network show good agreement with the experimental data. The mean square error value is  $4.04E-06$  that shows excellent performance of artificial neural network to predict thermal conductivity of COOH-functionalized MWCNTs/water nanofluid.

**Keywords** Thermal conductivity · MWCNTs/water · Artificial neural network · Nanofluid · Correlation

---

M. Hemmat Esfe (✉) · M. Akbari · M. Afrand · A. Karimipour  
Department of Mechanical Engineering, Najafabad Branch,  
Islamic Azad University, Isfahan, Iran  
e-mail: m.hemmatesfe@gmail.com

A. Naderi  
Semnan University, Semnan, Islamic Republic of Iran

## List of symbols

$k$	Thermal conductivity, $Wm^{-1} K^{-1}$
Re	Reynolds number
$T$	Temperature, K
MSE	Mean square error
RMSE	Root mean square error
MAE	Maximum absolute error
MLP	Feedforward multilayer perceptron

## Greek

$\varphi$	Solid volume fraction
-----------	-----------------------

## Subscripts

b	Base fluid
nf	Nanofluid
Pred	Predicted value
Exp	Experimental value

## Introduction

In recent years, applications of nanofluids have been developed in different thermal devices such as engine cooling, solar energy, nuclear reactors, cooling of electronic devices, and medical applications [1, 2].

Adding nanoparticles into fluids can be enhanced thermal conductivity of them. Therefore, a more compact system is possible using capable nanofluid. Appropriate type of nanoparticles plays a key role in obtaining a nanofluid with a high efficiency. Improving the heat transfer rate, using nanofluids consists of ultra-fine solid particle instead of usual fluids like water and oil is a proper solution.

A comprehensive model for the enhanced thermal conductivity of nanofluid has been presented by Wang [3]. Ghadimi et al. [4] presented a review of nanofluid stability

properties and characterization in stationary conditions. Gupta et al. [5] in a comprehensive review presented forced heat transfer characteristics with various nanofluids based on experimental investigation with constant heat flux and constant wall temperature boundary conditions in heat exchangers. Vajjha et al. [6] in a comprehensive evaluation determined the effects on the efficiency of nanofluids as a result of variation of density, specific heat thermal conductivity and viscosity, which are features of nanoparticle temperature and volume fraction.

Between the common nanoparticles, carbon nanotubes (CNTs) because of suitable thermal structure and properties have several advantages. For instance, using CNTs in common fluids makes the heat transfer better. An experimental survey has been done to study the turbulent flow of COOH-functionalized multi-walled CNTs/water nanofluid flowing through a double tube heat exchanger by Hemmat Esfe et al. [7]. Furthermore, Hemmat Esfe et al. [8] assessed the heat transfer features and pressure drop of low concentrations of a COOH-functionalized double-walled carbon nanotube (DWCNTs)/water nanofluid. Phuoc et al. [9] have also investigated thermal conductivity, viscosity and stability of nanofluids including multi-walled carbon nanotubes (MWCNTs) stabilized by cationic Chitosan. Nasiri et al. [10] studied influence of CNT structures on thermal conductivity and stability of nanofluid.

Diameter size, temperature and volume fraction are the factors that have been noticed in the nanofluids researches. In this ground, Hemmat Esfe et al. [11] conducted an experimental study on the thermal conductivity of  $\text{Al}_2\text{O}_3$ -water nanofluid. Using steady-state coaxial cylinders method, the thermal conductivity of  $\text{Al}_2\text{O}_3$ -water nanofluid was measured by Barbes et al. [12]. Using neural network method, Papari et al. [13] conducted a study to predict the thermal conductivity of various nanofluids. Their results showed that there is a great agreement between the results of modeling by neural network method and the other models available in the literature.

Some studies show that the diameter size of nanoparticles has reverse relation with thermal conductivity [14, 15]. Nasiri et al. [10] reported that smaller diameter of nanotubes has occasioned larger thermal conductivity. Furthermore, the most of the studies show that there is a direct relationship between temperature and thermal conductivity fraction [16, 17]. Additionally, there is a nonlinear relation between volume fraction and thermal conductivity of nanofluids in a direct way [7, 18].

Artificial neural network is a new method to predict nonlinear behavior of thermal conductivity ratio. Many researchers have studied an application of ANN in the modeling thermal conductivity in different nanofluids and thermophysical properties [13, 19, 20]. Hemmat Esfe et al. [21] investigated the thermal conductivity of MgO-EG

nanofluids using ANN; in addition, they suggested an empirical correlation to calculate the thermal conductivity ratio of MgO-EG nanofluids. A new correlation of dynamic viscosity of ZnO-EG nanofluids at different solid volume fraction and temperature based on experimental measurement has been presented by Hemmat Esfe et al. [16].

The target of the present study is to estimate thermal conductivity ratio of multi-walled carbon nanotubes (MWCNTs)/water nanofluid accurately using correlation and artificial neural networks.

## Experimental


Twenty-four data points for MWCNT covering a volume fraction ranging from 0.0005 to 0.01 and a temperature ranging from 25 to 55 °C have been used for developing models (Fig. 1) [22]. Properties of COOH-functionalized MWCNTs are presented in Table 1.

## Proposed new correlation

In this study, the thermal conductivity ratio of MWCNT were correlated as a function of solid volume fraction and temperature for the purpose of interpolation. The experimental data used as fitting pattern.

Nonlinear regression equation has employed to develop correlation model. Several equations drive out from nonlinear regression then the precise one chooses among them. In this article, in order to investigate the performance of the model, mean square error (MSE) and root mean square error (RMSE) were selected. The following equations are used to calculate the MSE and RMSE:

$$\text{MSE} = \frac{1}{N} \sum_{i=1}^N \left( \frac{K_{\text{nf}}}{K_{\text{b}}} \Big|_{\text{Exp},i} - \frac{K_{\text{nf}}}{K_{\text{b}}} \Big|_{\text{pred},i} \right)^2 \quad (1)$$



**Fig. 1** Thermal conductivity ratio via volume fraction in various temperature

**Table 1** Properties of COOH-functionalized MWCNTs

Purity/mass%	>97 (carbon content)
Inside diameter/nm	5–10
Length/um	10–30
Color	Black
True density/g cm <sup>-3</sup>	2.1

$$RMSE = \left[ \frac{1}{N} \sum_{i=1}^N \left( \left| \frac{K_{nf}}{K_b} \right|_{Exp,i} - \frac{K_{nf}}{K_b} \Big|_{pred,i} \right)^2 \right]^{1/2} \tag{2}$$

where N shows the number of experimental data,  $\frac{K_{nf}}{K_b} \Big|_{pred}$  is the predicted thermal conductivity ratio, and  $\frac{K_{nf}}{K_b} \Big|_{Exp}$  is the thermal conductivity ratio, which obtained from the experiment.

**Artificial neural network modeling**

The structure of human’s brain has been simulated by artificial neural network in computer. An ANN shows non-linear relation between inputs and outputs data by a connection between the neurons in pervious and next layers. Modeling complicated relation between data points is possible by using the ANN method.

In this study, thermal conductivity ratio of MWCNT was calculated in terms of temperature and volume fraction. Temperature and volume fraction were used as inputs to predict thermal conductivity ratio of MWCNT, and thermal conductivity ratio is taken into account as the output of the ANN.

Feedforward multilayer perceptron (MLP) was used as structure of ANN. This structure is one of the most applicable structures for prediction [19]. MLP have several layers with various neurons in each of them such as hidden layer and output layer. Neurons in each layer are connected to other neurons by mass coefficient. Outputs of neurons calculate by activation functions. Tangent sigmoid function was used as activation function of hidden layers, and pure linear function was used as activation function of output layer for an accurate prediction. MLP network consists of two hidden layers, and one output layer has been shown in Fig. 2. Each hidden layer has seven neuron, while output layer has one neuron.

In this article, back-propagation algorithm and Levenberg–Marquardt method have been used to predict thermal conductivity ratio of MWCNT. This algorithm commonly used for modeling [19].

Performance function is employed for assessing error during network training process. One of the most usual performance functions used in feedforward neural networks is MSE and RMSE (Eqs. 1 and 2) [13, 23, 24]. In

this study, MSE and RMSE have been employed to investigate ANN performance.

**Results and discussion**

Correlation model

A comparison of the performance functions values for different equation permits to choose the best modeling equation for describing thermal conductivity ratio of MWCNT in terms of solid volume fraction and temperature. According to MSE and RMSE values for various equations, Eq. 3 was chosen as the accurate equation.

$$\frac{K_{nf}}{K_b} = 0.9975 + 15.82 \times \varphi + 20.42 \times T \times \varphi^2 + 0.005983 \times \varphi \times T^2 - \varphi \times \cos(19.43 \times T \times \varphi) \tag{3}$$

The performance of Eq. 3 via several performance functions has been shown in Table 2.

The thermal conductivity ratio of MWCNT obtained by experimental and correlation has been compared in variety volume fractions and temperatures (Figs. 3, 4).


As it can be seen, the correlation coefficient is very close to one, which shows that there is sufficient adjustment between correlation and experimental data. In addition, maximum error is 0.0055, which occurs in volume fraction 0.01 and temperature 35 °C, which shows that correlation has adequate accuracy to predict thermal conductivity ratio.

ANN model

Thermal conductivity ratio of MWCNT was calculated in solid volume fraction from 0.05 to 1 % and temperature from 25 to 35 °C (Fig. 1). From 24 data points, 18 were used for training and remaining data points were used for testing and validation of network. It is better to normalize data in [−1 1] interval to better network training.

Fourteen networks were used to choose adequate structure. Optimum number of neurons in the hidden layer is selected by trying various network structures and compares their MSE and RMSE values. The ANN structure with lowest MSE and RMSE was selected as the optimum structure. Values of MSE and RMSE for various structures have been shown in Table 3. Based on Table 3, the structure with seven neurons in each hidden layer has the lowest MSE and RMSE value. This structure was chosen as the best structure to predict thermal conductivity ratio in terms of volume fraction and temperature with MSE and RMSE value equal to  $4.04 \times 10^{-6}$  and 0.002, respectively.

**Fig. 2** MLP network consist of two hidden layers and one output layer




**Table 2** Performance of correlated model

Mean square error	$9.7415238 \times 10^{-6}$
Root mean square error	0.0019
Maximum absolute error	0.0055
Correlation coefficient	0.99973063


**Table 3** MSE value for various ANN structure

Number of hidden layers	Number of neurons in each hidden layer	MSE	RMSE
1	2	6.36E-05	0.008
1	3	3.61E-05	0.006
1	4	1.61E-05	0.004
1	5	3.27E-05	0.0057
1	6	5.60E-06	0.0024
1	7	3.71E-05	0.0061
1	8	3.00E-05	0.0055
2	2	1.41E-05	0.0038
2	3	1.06E-05	0.0033
2	4	6.08E-05	0.0078
2	5	9.03E-05	0.0095
2	6	4.56E-05	0.0067
2	7	<b>4.04E-06</b>	<b>0.002</b>
2	8	4.91E-05	0.007



**Fig. 3** Regression diagram of correlated model

The bold value shows best structure with lowest error




**Fig. 4** Comparison between experimental results and correlated model

Regression diagram of trained neural network has been shown in Fig. 5. This figure shows that there is excellent agreement between experimental results and ANN model outputs.


Figure 6 shows comparison between experimental results and ANN model outputs. The maximum error is 0.0064, which occurs at temperature 25 °C and volume fraction 0.008. As it can be seen, there is good fitness between experimental results and ANN model outputs.

**Comparison between experimental results and models**


In Figs. 7 and 8, thermal conductivity ratio of MWCNT/water nanofluid obtained by experiment, correlation and ANN model has been compared. It can clearly found that the results of experiment and both models are very close together.




**Fig. 5** Regression diagram of trained neural network



**Fig. 8** Parity plot and thermal conductivity ratio prediction for MCWNT



**Fig. 6** Comparison between experimental results and ANN model outputs



**Fig. 7** Comparison between thermal conductivity ratio obtained by experiment, correlation and ANN

As a result, there is sufficient adjustment between experimental results and models outputs. Although ANN model has better performance than correlation, it is possible to use these reliable models to estimate thermal conductivity ratio of MWCNT/water nanofluid, precisely.

### Conclusions

The aim of the present study is to estimate thermal conductivity ratio of multi-walled carbon nanotubes (MWCNTs)/water nanofluid accurately using correlation and artificial neural networks.

It has been suggested an equation (Eq. 3) by nonlinear regression with MSE equal to  $9.7415238 \times 10^{-6}$ , RMSE equal to 0.0019, and the maximum absolute error is 0.0055. Based on performance functions value, this method has an appropriate ability to model thermal conductivity ratio of MWCNTs/water nanofluid, accurately.

Furthermore, artificial neural network has been used to predict thermal conductivity ratio of MWCNTs/water nanofluid. In order to obtain the best structure with lowest performance function, a MLP network with two hidden layers and seven neurons in each hidden layer has been selected as optimal structure. The values of MSE and RMSE are  $4.04 \times 10^{-6}$  and 0.002, respectively. Obviously, it can be found that ANN model has a good ability to predict thermal conductivity ratio of MWCNT in term of volume fraction and temperature with adequate accuracy. In addition, ANN model has better prediction than correlation in order to estimate thermal conductivity ratio.

Therefore, it can be noticed that the presented models have a good ability to estimate thermal conductivity ratio of MWCNTs/water nanofluid. Further studies aimed to elucidate the precise nature of this new class of heat transfer fluids (called as nanofluids) would be of considerable interest. The extension of this paper and our previous work [25–29] affords engineers a good option for nanofluid in applications such as electronics, automotive, and nuclear applications where improved heat transfer or efficient heat dissipation is required. Also, future studies aimed at elucidating the precise nature of nanofluid heat transfer would be of considerable interest.

## References

- Saidur R, Leong KY. A review on applications and challenges of nanofluids. *Renew Sustain Energy Rev.* 2011;15:1646–68.
- Mahian O, Kianifar A, Kalogirou SA, Pop I, Wongwises S. A review of the applications of nanofluids in solar energy. *Int J Heat Mass Transf.* 2013;57:582–94.
- Wang W. A comprehensive model for the enhanced thermal conductivity of nanofluids. *J Adv Res Phys.* 2012;3:5.
- Ghadimi A, Saidur R, Metselaer HSC. A review of nanofluid stability properties and characterization in stationary conditions. *Int J Heat Mass Transf.* 2011;54:4051–68.
- Gupta M, Arora N, Kumar R, Kumar S, Dilbaghi N. A comprehensive review of experimental investigations of forced convective heat transfer characteristics for various nanofluids. *Int J Mech Mater Eng.* 2014;9:1–21.
- Vajjha RS, Das DK. A review and analysis on influence of temperature and concentration of nanofluids on thermophysical properties, heat transfer and pumping power. *Int J Heat Mass Transf.* 2012;55:4063–78.
- Hemmat Esfe M, Saedodin S, Mahian O, Wongwises S. Thermophysical properties, heat transfer and pressure drop of COOH-functionalized multi walled carbon nanotubes/water nanofluids. *Int Commun Heat Mass Transf.* 2014;58:176–83.
- Hemmat Esfe M, Saedodin S, Mahian O, Wongwises S. Heat transfer characteristics and pressure drop of COOH-functionalized DWCNTs/water nanofluid in turbulent flow at low concentrations. *Int J Heat Mass Transf.* 2014;73:186–94.
- Phuoc TX, Massoudi M, Chen RH. Viscosity and thermal conductivity of nanofluids containing multi-walled carbon nanotubes stabilized by chitosan. *Int J Therm Sci.* 2011;50:12–8.
- Nasiri A, Shariaty-Niasar M, Rashidi AM, Khodafarin R. Effect of CNT structures on thermal conductivity and stability of nanofluid. *Int J Heat Mass Transf.* 2012;55:1529–35.
- Hemmat Esfe M, Saedodin S, Mahian O, Wongwises S. Thermal conductivity of  $\text{Al}_2\text{O}_3$ /water nanofluids Measurement, correlation, sensitivity analysis, and comparisons with literature reports. *J Therm Anal Calorim.* 2014;117:675–81. doi:10.1007/s10973-014-3771-x.
- Barbés B, Páramo R, Blanco E, Pastoriza-Gallego MJ, Piñeiro MM, Legido JL, Casanova C. Thermal conductivity and specific heat capacity measurements of  $\text{Al}_2\text{O}_3$  nanofluids. *J Thermal Anal Calorim.* 2013;11:1615–25.
- Papari MM, Yousefi F, Moghadasi J, Karimi H, Campo A. Modeling thermal conductivity augmentation of nanofluids using diffusion neural networks. *Int J Therm Sci.* 2011;50:44–52.
- Hemmat Esfe M, Saedodin S, Mahian M, Wongwises S. Efficiency of ferromagnetic nanoparticles suspended in ethylene glycol for applications in energy devices: effects of particle size, temperature, and concentration. *Int Commun Heat Mass Transf.* 2014;58:138–46.
- Sundar LS, Sharma KV, Naik MT, Singh MK. Empirical and theoretical correlations on viscosity of nanofluids: a review. *Renew Sustain Energy Rev.* 2013;25:670–86.
- Hemmat Esfe M, Saedodin S. An experimental investigation and new correlation of viscosity of ZnO—EG nanofluid at various temperatures and different solid volume fractions. *Exp Therm Fluid Sci.* 2014;55:1–5.
- Khaleduzzaman SS, Mahbulul IM, Shahrul IM, Saidur R. Effect of particle concentration, temperature and surfactant on surface tension of nanofluids. *Int Commun Heat Mass Transf.* 2013;49:110–4.
- Hemmat Esfe M, Saedodin S, Asadi M, Karimipour A. Thermal conductivity and viscosity of  $\text{Mg}(\text{OH})_2$ -ethylene glycol nanofluids: finding a critical temperature. *J Therm Anal Calorim.* doi:10.1007/s10973-015-4417-3.
- Kurt H, Kayfeci M. Prediction of thermal conductivity of ethylene glycol–water solutions by using artificial neural networks. *Appl Energy.* 2009;86:2244–8.
- Hojjat M, Etemad SG, Bagheri R, Thibault J. Thermal conductivity of non-Newtonian nanofluids: experimental data and modeling using neural network. *Int J Heat Mass Transf.* 2011;54:1017–23.
- Hemmat Esfe M, Saedodin S, Bahiraei M, Toghraie D, Mahian O, Wongwises W. Thermal conductivity modeling of MgO/EG nanofluids using experimental data and artificial neural network. *J Therm Anal Calorim.* 2014;118:287–94.
- Hemmat Esfe M, Saedodin S, Mahian O, Wongwises S. Thermophysical properties, heat transfer and pressure drop of COOH-functionalized multi walled carbon nanotubes/water nanofluid. *Int Commun Heat Mass Transfer.* 2014;58:176–83.
- Longo GA, Zilio C, Ceseracciu E, Reggiani M. Application of artificial neural network (ANN) for the prediction of thermal conductivity of oxide–water nanofluids. *Nano Energy.* 2012;1:290–6.
- Di Nicola G, Ciarrocchi E, Coccia G. Correlations of thermal conductivity for liquid refrigerants at atmospheric pressure or near saturation. *Int J Refrig.* 2014;45:168–76.
- Hemmat Esfe M, Saedodin S, Mahmoodi M. Experimental studies on the convective heat transfer performance and thermophysical properties of MgO–water nanofluid under turbulent flow. *Exp Therm Fluid Sci.* 2014;52:68–78.
- Hemmat Esfe M, Saedodin S. Turbulent forced convection heat transfer and thermophysical properties of MgO–water nanofluid with consideration of different nanoparticles diameter, an empirical study. *J Therm Anal Calorim.* doi:10.1007/s10973-014-4197-1.
- Hemmat Esfe M, Saedodin S, Asadi A. An empirical investigation on the dynamic viscosity of  $\text{Mg}(\text{OH})_2$ -ethylene glycol in different solid concentrations and proposing new correlation based on experimental data. *Int J Nat Eng Sci.* 2014;8(3):29–34.
- Hemmat Esfe M, Zare Ghadi A, Mirtalebi Esforjani SS, Akbari M. Combined convection in a lid-driven cavity with an inside obstacle subjected to  $\text{Al}_2\text{O}_3$ -water nanofluid: effect of solid volume fraction and nanofluid variable properties. *Acta Phys Pol A.* 2013;12(4):665–72. doi:10.12693/APhysPolA.124.665.
- Hemmat Esfe M, Niazi S, Sadegh Mirtalebi Esforjani S, Akbari M. Mixed convection flow and heat transfer in a ventilated inclined cavity containing hot obstacles subjected to a nanofluid. *Heat Transf Res.* 2014;45(4):309–38.